

Eterna-Seal

RUBBERIZED ALUMINUM COATING

7145-7



PHYSICAL PROPERTIES:

RUBBERIZED ALUMINUM COATING is a bright metallic, non-asphaltic, fibered aluminum coating formulated for a variety of roof surfaces. In addition to the waterproofing protection, heat reflection, and attractive aluminum color. This product has also been specifically designed to withstand fading and will not brown out as often occurs when asphaltic aluminum coatings are exposed to moisture. Refer to published guide specifications for additional details.

SPECIFICATIONS

Flash Point	105°F
Non-Volatile Liquid Elastomer	25-35%
% Aluminum Pigment	33-40%
% Solvents	42-55%
Container Stability	1 year
Weight/Gallon	7.65lbs.

TYPICAL PROPERTIES OF CURED COATINGS*

Dry Time	
To Touch	2-3 hours
Throughout, Days @72° F	3
Film Thickness of 1 gal/100 square feet	5 mils
Color Stability	Excellent
Elongation. ASTM D-412	
At 77°F	200%
At 32°F	100%
Tensile Strength. ASTM D-412	200 psi
Temperature Range	
Application Degree F	40/120° F
Service Degree F.	-40/180° F
Resistance to:	
Sunlight	Good
Chemicals	Excellent
Ozone	Excellent
Permeability, Water Vapor ASTM E-96	0.2 perms
Weathering Effect	Excellent
Adhesion	
Hypalon and EPDM	Good
Aluminum	Excellent
Steel	Excellent
Cold Temperature Flexibility	Excellent
Abrasion Resistance	Excellent
Resistance, Foot Traffic	Excellent

7145-7

TRUCO, INC.
4301 Train Avenue
Cleveland, Ohio 44113
www.truco-inc.com

Energy Star® Partner,
TRUCO, Inc. has determined
that this product meets
the Energy Star® guidelines
for energy efficiency.

